From the house of ALSTONE

WATER PROOF PLY

101% GENUINE WATER PROOF PLY

ALSTONE
WATER PROOF PLY

TECHNICAL SPECIFICATIONS	
Property	**Test results**
Edge Straightness (%)	0.20
Squareness (%)	0.20
Dimensional Changes caused by	
Humidity at 90+ / - 5% (RH & Temp. 270C)	
A) Difference in Length	+/-1 mm
c) Difference in Thickness	+/-1 mm
Dimensional Changes caused by	
Humidity at 40+/- 5% (RH & Temp. 270C)	
a) Difference in Length	+/-1 mm
b) Difference in Thickness	+/-1 mm
Resistance to Water	Excellent
Adhesion of plies	Excellent
Modulus of Rupture N/mm2	
A) Average	58
B) Min-Individual	51
Modulus of Elasticity N/mm2	
A) Average	6200
B Min-Individual	4900
Mycological test	No Delamination at edge
Spot Test	PVC Polymer Based

Complete PAISA WASOOL Ply

(Green Rating for Integrated Habitat Assessment)

LIFE TIME GUARANTEE LIFE TIME

ALSTONE
Alstone Industries Pvt. Ltd.

www.alstone.industries

Corporate Office: Alstone House, 2E/7, Jhandewalan Extn., New Delhi-110055 Tel: 011-41232400 (50 Lines)
Fax: +91-11-41232412 Toll Free: 1800-123-3123 Email: wpc@alstoneindia.com, ask@alstoneindia.com
Branch Office: • Banglore • Noida • Kochi • Pune